"De officiele Saft dealer in Nederland"

Primary lithium batteries LSH 26180

3.6V Primary lithium-thionyl chloride (Li-SOCl₂) High power ¹/₃ C-size spiral cell

For high drain/high pulse applications requesting superior voltage response and operating life in -60°C/+85°C environments.



Key features

- High and stable operating voltage
- Superior drain capability
- Low self-discharge rate (less than 3% after 1 year of storage at +20°C)
- Stainless steel container
- Hermetic glass-to-metal sealing
- Built-in safety vent
- Finish with 5 A fuse
- Non-flammable electrolyte
- Non-restricted for transport

Main applications

- Radiocommunication and other military applications
- Night vision
- Beacons and emergency location transmitters
- Tracking systems

etc...


NATO stock number (PS 31 A finish) 6135 14 376 4875

Cell size references	1/3 UM2 - 1/3 R14 - 1/3 C
Electrical characteristics	
(typical values relative to cells stored for one year or le	ess at + 30°C max.)
Nominal capacity (at 10 mA + 20 °C 2.0V cut off. The capacity restore according to current drain, temperature and cut off).	1 . 2 Ah ed by the cell varies
Open circuit voltage (at +20°C)	3.67V
Nominal voltage (at 0.5 mA +20°C)	3.6V
Pulse capability: Typically up to 700 mA (700 mA drained every 2 mn at + 20 °C from undischarged cells current, yield voltage readings above 3.0 V. The reading to the pulse characteristics, the temperature, and the Fitting the cell with a capacitor may be recommended Consult Saft)	gs may vary according cell's previous history.
Continuous current permitting 50% of the nominal ca achieved at +20°C with 2.0V cut off. (Higher currents possible, consult Saft)	pacity to be 400 mA
Storage (recommended) (for more severe condition:	+ 30°C (+ 86°F) max s, consult Saft)
Operating temperature range (Operation above ambient T may lead to reduced capal lower voltage readings at the beginning of pulses. Con	
Physical characteristics	
Diameter (max)	26.2 mm (1.03 in)
Height (max)	18.6 mm (0.73 in)
Typical weight	24 g (0.9 oz)
Li metal content	approx 0.3 g
Available termination suffix CN, CNR	radial tabs
3 PF, 3 PF RP CNA (AX)	radial pins axial leads


flying leads ...etc.




LSH 26180



Dimensions in mm.



Voltage plateau versus Current and Temperature (at mid-discharge)




Typical discharge profiles at + 20°C

Storage

 The storage area should be clean, cool (not exceeding + 30°C), dry and ventilated.

Warning

- Fire, explosion and severe burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell.



Restored Capacity versus Current and Temperature (2.0 V cut off)

Saft

12, rue Sadi Carnot 93170 Bagnolet - France Tel +33 1 49 93 19 18 Fax +33 1 49 93 19 69

www.saftbatteries.com

Doc. Nº 31018-2-0904 Published by the Communications Department

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2-0604. Photo credit: Saft

Produced by Arthur Associates

Société anonyme au capital de 31 944 000€ RCS Bobigny B 383 703 873

